

<b>International standards</b>	Material No.	2.4648
	DIN 1736	EL-NiCr 19 Nb
	DIN EN ISO 14172	E Ni 6082 (NiCr20Mn3Nb)
	AWS A5.11	E NiCrFe-2 / mod.

**Approvals** TÜV

**Typical applications and characteristics** Basic-coated nickel base electrode with an alloyed core wire. Suitable for joining and cladding low alloyed and alloyed steels, welding iron- and nickel base alloys and for dissimilar joints.  
The austenitic deposit is insensitive to hot-cracking and free of embrittlement at high as well as at low temperatures, non-scaling up to 1000° C, and cold tough down to -196° C.  
No diffusion of carbon into the weld metal at high temperatures.  
Used for service-temperatures of more than 300° C in Chemical Industry, Petrochemical Industry, glassworks, civil engineering, repairing and maintenance workshops.

**Operating temperature** - 196° C up to 550° C

<b>Base materials</b>	2.4605 NiCr23Mo16Al	2.4856 NiCr22	2.4952 NiCr20TiAl
	2.4630 NiCr20Ti	Mo9Nb	1.4876 X10NiCrAlTi32-20
	2.4631 NiCr20TiAl	2.4858 NiCr21Mo	(Alloy 800)
	2.4669 NiCr15Fe7TiAl	2.4867 NiCr60-15	1.4958 X5NiCrAlTi31-20
	2.4816 NiCr15Fe	2.4858 NiCr21Mo	1.4959 X8NiCrAlTi32-21
	2.4817 LC-NiCr15Fe	2.4869 NiCr80-20	(Alloy 800 HT)
	2.4851 NiCr23Fe	2.4870 NiCr 10	
		2.4851 NiCr23Fe	

Dissimilar joints:

Ni-base alloys to austenitic steels/ Ni-base alloys to ferritic steels/ austenitic to ferritic steels up to 550° C

<b>Mechanical properties of all-weld metal</b>	<b>Tensile strength</b>	<b>Yield strength</b>	<b>Elongation</b>	<b>Impact strength</b>
	<b>R<sub>m</sub> N/mm<sup>2</sup></b>	<b>R<sub>p0,2</sub> N/mm<sup>2</sup></b>	<b>A<sub>5</sub> %</b>	<b>ISO – V J at -196° C</b>
( typical values)	700	420	42	96

<b>Weld metal analysis</b> (typical, wt. %)	<b>C</b>	<b>Mn</b>	<b>Mo</b>	<b>Cr</b>	<b>Ni</b>	<b>Fe</b>	<b>Nb</b>
	< 0,04	4,5	<1	19	Bal.	< 4	2

**Current** = +

**Welding positions** PA, PB, PC, PD, PE, PF

**Rebaking** 1 h, 350 °C + / - 10 °C ( if required )

Dia./Length	Amperage (A)	Pcs./ packet	Pcs./ carton	kg / 1000	kg / packet	kg / carton
2,5 x 300	50 - 90	244	976	16,5	4,0	16,0
3,2 x 350	70 - 120	153	612	32,5	5,0	20,0
4,0 x 350	100 - 160	102	408	49,5	5,0	20,0
5,0 x 450	140 - 200	60	240	100,0	6,0	24,0

Rev. 002/12

Statements on composition and application are just for the applier's information. Statements on mechanical properties always refer to the all-weld-metal according to valid standards. Carbo-Weld may change the characteristics of its products without notice. We recommend the applier to check our products for their special application autonomously.